

Technical Data Sheet

comp

Masonry, repair and shaft head mortar

SC-TD-AwaTec comp E-Rev 02

Issue: 07/2018

Product description

SC-AwaTec® „comp“ is a cement-based, polymer-modified one-component masonry and shaft head as well as repair mortar for sewer construction and sewer rehabilitation.

Areas of application

- Wastewater and purification plants
- Placing of manhole covers, manhole rings and paving stones
- Potable water protection zones
- Usable from pH 4,5 to pH 10

Properties

- Fibre-reinforced
- Resistant to frost and de-icing salt
- Early strength development
- Non-shrink
- Traffic load carrying capacity after 2 hours
- Impermeable to water, thus sealing against pressing groundwater

Processing guidelines

Surface preparation

- The surface has to be free from loose particles, grease, oil, cement grout or any other adhesion-reducing substances.
- The surface may be concrete, brickwork or unglazed stoneware.
- Water jet or solid jet is required to prepare a suitable surface.
- The surface has to be pale damp, but essentially without a flowing water film.

Mixing

- Only mix using suitable stirring device.
- Water requirement: approx. 11 % to 12 % per 25 kg-bag, corresponding to 2,7 to 3,0 litres of drinking water per 25 kg-bag.
- Prepare water, then steadily add mortar, while mixer running slowly.
- Mixing time: min. 3 minutes, until a uniform mixture is achieved.

Processing time (open time)

- Max. 15 minutes (at 20 °C) from first addition of water.
- Higher temperatures will shorten the open time, lower temperatures will prolong the open time.

Technical Data Sheet

comp

Masonry, repair and shaft head mortar

SC-TD-AwaTec comp E-Rev 02

Issue: 07/2018

Method of Application

- SC-AwaTec® „comp“ can be applied manually.

Post-treatment

- The surface coated with SC-AwaTec® „comp“ has to be protected against premature drying out by draught and heat. Post-treatment should last at least 7 days and correspond to DWA-M 143-17.
- Suitable post-treatment measures are fabric covering, plastic film, keeping the surface moist, or suitable curing agents.

Safety instructions

- Please observe the safety instructions and recommendations to be taken from the SC-AwaTec® Material Safety Data Sheet.

Technical properties

Compressive strength:	after 2 hours	8 N/mm ²
	after 1 day	25 N/mm ²
	after 7 days	45 N/mm ²
	after 28 days	55 N/mm ²
Consumption:	approx. 20 kg/m ² at 10 mm layer thickness	
Granulation:	< 2 mm	

Further characteristics

Colour shade:	grey
Unit size:	25 kg-bag
Processing temperature:	+5 °C to +30 °C
Storage:	dry
Shelf life:	12 months from date of manufacture

Remarks:

The indications contained in this technical product data sheet are product descriptions. They represent general information and are based on trials, tests and practical experience. The values are average values, determined at standardized climate to DIN EN 23270 (23°C/50% r.F.). Deviations cannot be ruled out. When applying our mortars, the individual processing guidelines, relevant directives, recommendations and standards have to be observed. In any case, generally recognized standards of technology have to be respected and adhered to. If necessary, tests should be carried out prior to specific applications. We reserve the right to amend technical details at any time. With this issue, all previous technical data sheets become invalid. Issue: 07/2018